

Specification Sheet

ZSZS PP Top NG WH

Face:

Biaxially orientated, gloss polypropylène film with a print-receptive topcoating.

Thickness	60 micron
Basic Weight	47g/m ²

Adhesive:

The adhesive features excellent tack and adhesion on a wide variety of substrates, including apolar, slightly rough and curved substrates. Particularly good performance at lower temperatures, eg. labelling of chilled products. The adhesive complies with European food directives and legislations, FDA 175.105 and the German recommendations XXI as published by BfR. BfR is the German Federal Institute for Risk Assessment. The adhesive can be used in direct contact with dry and moist, non fatty foodstuffs.

Initial Tack	700N/m
Peel Adhes. 90°	370N/m
Min. App. Temp	0°C
Temp Range	-40°C to +80°C

BS 5609 Section Two Part 4.1 : Marine Exposure.

Liner:

BG40 white, a supercalendered glassine paper.

Thickness	55 micron
Basic Weight	62 g/m ²

Laminate: Total Thickness: 132 micron

Shelf Life:

2 years when stored at 22°C / 50% RH.

The above specification is based on information obtained from the original manufacturer and is offered in good faith in accordance with the company's conditions to determine fitness for use. No guarantee is offered or implied. It is the ultimate user's responsibility to fully test the material and determine its suitability for the application intended. Measurements and test results are nominal. In accordance with a policy of continuous product improvement the manufacturer reserves the right to amend the specification without notice.